

## Espuma de PVC 200



Densidad kg/m <sup>3</sup>	ASTM D1622	kg/m <sup>3</sup>	nominal	200
Resistencia a la compresión	ASTM D1621-10	MPa	average min-ave min-min	4,84 4,64 4,00
Modulo de compresión	ASTM D1621-10	MPa	average min-ave min-min	212 198 172
Resistencia a la rotura	ASTM D1623	MPa	average min-ave min-min	6,61 5,61 5,33
Modulo de rotura	ASTM D1623	MPa	average min-ave min-min	415 343 317
Resistencia al corte	ASTM C273	MPa	average min-ave min-min	3,59 3,23 2,81
Modulo de corte	ASTM C273	MPa	average min-ave min-min	78 74 65
Alargamiento de corte a la rotura	ASTM C273	%	average	41
Medidas estandar		mm		750 1600 48